

## ERISYS™ GE-60

Sorbitol Glycidyl Ether -

Aliphatic Polyfunctional Epoxy Resin

CAS NO. 68412-01-1

### DESCRIPTION

ERISYS GE-60, epoxidized sorbitol, is an aliphatic multifunctional epoxy resin. This resin will impart both higher reactivity and crosslink density to epoxy resin formulations.

Additionally, ERISYS GE-60 can be used to crosslink acid functional polyurethane and acrylic resins for improved chemical resistance in light stable coatings.

### APPLICATIONS

- ☐ Crosslinker for Acrylic and Polyurethane Resins
- ☐ Accelerator for Epoxy Resins

### TYPICAL PROPERTIES

Appearance	Clear, Clean
Viscosity @ 25°C, cps	8,000 – 18,000
Epoxide Equivalent Weight, g/eq	160 - 195
Gardner Color, max	2
Residual Epichlorohydrin, max ppm	50
Hydrolyzable Chloride, max %	0.50
Weight per Gallon, @ 25°C lbs.	10.7 ± 0.1
Flash Point, °C (°F)	>160 (>320)

### HEALTH & SAFETY PRECAUTIONS

ERISYS GE-60 is not a primary skin irritant or sensitizer. However, as with any epoxy material, irritation can result from repeated or prolonged contact. The symptoms of this irritation may appear as a mild reddening or a more pronounced rash. It is, therefore, important to avoid skin contact where possible. Butyl rubber gloves, full eye protection and protective clothing are recommended.

Refer to **CVC Thermoset Specialties** Material Safety Data Sheet on ERISYS GE-60 for additional safety and health information. The MSDS is revised as new data becomes available.

### PACKAGING & AVAILABILITY

ERISYS GE-60 is available in 55 gal. non-returnable steel drums (net weight 480 lbs.) and 5 gal. plastic pails (45 lbs. net). Bulk shipments are available with adequate lead-time. Drum inventory is available at most CVC regional warehouses. Check with your local sales representative for the shipping location nearest you.



**An Emerald Performance Materials Company**

**ERISYS™ GE-60**

## **DISCLAIMER**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.

CVC Thermoset Specialties—844 N. Lenola Road/Moorestown, NJ 08057  
An Emerald Performance Materials Company

© Copyright 2006 Emerald Performance Materials LLC. 6/2006

**CVC Thermoset Specialties**

844 North Lenola Road / Moorestown, NJ 08057 / Phone: 856-533-3000 / Fax: 856-533-3003 / [www.emeraldmaterials.com](http://www.emeraldmaterials.com)