

# ERISYS™ GS-120

Dimer Acid Diglycidyl Ester  
CAS NO. 68475-94-5  
EINECS - 500-215-4

## DESCRIPTION

ERISYS GS-120 is the diepoxide of a long chain aliphatic dimer acid. GS-120 is expected to find utility as a reactive additive which imparts a degree of flexibility to normally rigid epoxy systems. The low viscosity of GS-120 will reduce the viscosity of your formulation, allowing for increased filler loading and improved handling. GS-120 will increase toughness and tensile elongation, and improve impact and thermal shock resistance. Improvements in tensile shear and peel adhesion will also be realized. These benefits are achieved, however, with some sacrifice in elevated temperature performance and chemical resistance.

GS-120 is typically used as a flexibilizing diluent with liquid DGEBA resins such as EPALLOY 7190. It is also ideally suited for use as a reactive diluent for use with HyPox™ DA323, a dimer adduct of DGEBA resin. In combination with other resins the possibility of forming incompatible blends exists and, therefore, the use of GS-120 may have to be avoided for some applications.

EPALLOY 7190/GS-120 blends can be cured with all typical epoxy curing agents except epoxy/amine adducts, where incompatible cured formulations may result.


## APPLICATIONS

- ☐ Floor coatings
- ☐ Adhesives
- ☐ Potting compounds
- ☐ Laminating
- ☐ Filament winding
- ☐ Grouts
- ☐ Joint Sealants

## TYPICAL PROPERTIES


Appearance	Clear, Clean
Viscosity @ 25°C, cps	400 – 900
Epoxide Equivalent Weight, g/eq	390 – 470
Gardner Color, max	9
Weight per Gallon, @ 25°C, lbs.	8.2 ± 0.1
Flash Point, °C (°F)	>93.3 (>200)

## VISCOSITY AND POT LIFE




## THE EFFECT OF ERISYS GS-120 ON THE CURED PROPERTIES OF LIQUID EPOXY RESIN (EEW 188) CURED WITH TETA


### Tg and WATER ABSORPTION




### TENSILE PROPERTIES



### FLEXURAL PROPERTIES




### COMPRESSIVE STRENGTH and HARDNESS




Physical Properties Report		GS-120 in Epalloy 7190			
Epalloy 7190	100	95	90	80	70
Erisys GS-120	0	5	10	20	30
TETA	13	12.6	12.3	11.6	10.9
Resin Viscosity @ 25°C (cps)	12,700	8,125	5,875	3,500	2,400
100 gram gel time (mins)	42	43	44	47	57
Tensile Strength (psi)	11,357	9,197	9,042	8,806	7,319
Tensile Elongation (%)	8.1	6.8	6.1	8.8	13.4
Tensile Modulus (psi x 10 <sup>5</sup> )	2.00	1.80	1.84	1.59	1.36
Flexural Strength (psi)	12,687	12,953	11,627	10,099	9,335
Flexural Modulus (psi x 10 <sup>5</sup> )	3.51	3.06	2.86	2.51	2.15
Compressive Yield Strength	15,552	14,347	13,820	12,280	10,606
Compressive Modulus (psi x 10 <sup>5</sup> )	2.29	2.34	2.21	2.08	1.76
Shore D Hardness	85	83	81	83	81
Tg (°C)	116	114	110	101	88
Water Absorption (28 days @ RT)	0.3	0.7	0.8	1.0	1.1
Water Absorption (2 hour boil)	0.4	0.7	1.0	1.3	1.4

## THE EFFECT OF ERISYS GS-120 ON THE CURED PROPERTIES OF LIQUID EPOXY RESIN (EEW 188) CURED WITH ANCAMIDE 502 FOR A FLEXIBILIZED FORMULATION


### POT LIFE and HARDNESS




### TENSILE PROPERTIES



### FLEXURAL PROPERTIES



### COMPRESSIVE STRENGTH and WATER ABSORPTION



Physical Properties Report		GS-120 with Ancamide 502			
Epalloy 7190	100	95	90	80	70
Erisys GS-120	0	5	10	20	30
Ancamide 502	48.6	47.3	46.0	43.3	40.7
Resin Viscosity @ 25°C (cps)	12,700	7,800	5,500	3,200	2,000
100 gram gel time (mins)	174	163	220	250	288
Tensile Strength (psi)	7,803	7,437	6,932	5,751	4,652
Tensile Elongation (%)	10.4	11.2	14.1	23.6	31.9
Tensile Modulus (psi x 10 <sup>5</sup> )	1.41	1.35	1.24	1.07	0.86
Flexural Strength (psi)	10,370	9,381	8,700	6,620	4,834
Flexural Modulus (psi x 10 <sup>5</sup> )	2.62	2.34	2.19	1.68	1.15
Compressive Yield Strength	9,511	8,928	8,196	6,797	5,197
Compressive Modulus (psi x 10 <sup>5</sup> )	1.91	1.86	1.72	1.40	1.13
Shore D Hardness	85	82	80	76	63
Water Absorption (28 days @ RT)	0.9	1.3	1.5	1.9	2.2
Water Absorption (2 hour boil)	1.1	1.2	1.5	1.8	2.0



An Emerald Performance Materials Company

ERISYS™ GS-120

## **HEALTH & SAFETY PRECAUTIONS**

ERISYS GS-120 is not a primary skin irritant or sensitizer. However, as with any epoxy material, irritation can result from repeated or prolonged contact. The symptoms of this irritation may appear as a mild reddening or a more pronounced rash. It is, therefore, important to avoid skin contact where possible. Chemical resistant gloves, full eye protection and protective clothing are recommended.

Refer to **CVC Thermoset Specialties** Material Safety Data Sheet on ERISYS GS-120 for additional safety & handling information. The MSDS is revised as new data becomes available.

## **PACKAGING & AVAILABILITY**

ERISYS GS-120 is available in 55 gal. non-returnable steel drums (net weight 440 lbs.) and 5 gal. plastic pails (40 lbs. net). Bulk shipments are available with adequate lead-time. Drum inventory is available at most CVC regional warehouses. Check with your local sales representative for the shipping location nearest you.

## **DISCLAIMER**

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.

CVC Thermoset Specialties—844 N. Lenola Road/Moorestown, NJ 08057  
An Emerald Performance Materials Company

© Copyright 2006 Emerald Performance Materials LLC. 6/2006

**CVC Thermoset Specialties**

844 North Lenola Road / Moorestown, NJ 08057 / Phone: 856-533-3000 / Fax: 856-533-3003 / [www.emeraldmaterials.com](http://www.emeraldmaterials.com)